



AquataPoxy A-61

DESCRIPTION

AquataPoxy® A-61 is a solvent-free, 100% solids, high build epoxy coating, formulated for broad range corrosion protection, A-61 is also certified safe for cold potable water with a 5 hour cure time.

TYPICAL USES

Formulated for use on surfaces where corrosion and water resistance is needed, including:

- Water distribution and transmission lines 30" and larger
- Water tanks 50 gallons and larger
- Water treatment storage reservoirs
- Pharmaceutical and food facilities
- General maintenance

COLOR

The standard Part A Resin is white; the Part B Curing Agent is green. When mixed the product is aqua. The Part B is also available in a translucent brown, when used with white Part A; the mixed product is a white color.

SOLIDS BY VOLUME

100% solids by volume
Volatile Organic Compounds: 0.0 pounds per gallon

FILM THICKNESS

AquataPoxy A-61 is a 100% solids epoxy with zero shrinkage. Wet film thickness and dry film thickness are the same (i.e. 40 mils WFT = 40 mils DFT). Depending on substrate type and profile, a maximum of 120 mils per coat is recommended to prevent sagging. Typical recommended thickness for immersion duty is 25-80 mils on metal and 60-120 mils on concrete.

ANSI/NSF 61 maximum dry film thickness for pipes 30 inches or bigger; or for tanks 50 gallons and larger: 120 mils.

COVERAGE

Theoretical coverage is 40 square feet per gallon at 40 mils wet film thickness. Actual surface coverage will depend on substrate porosity and roughness. Good painting practices suggest application of two coats for quality assurance. A wet film thickness gauge may be used to determine actual coating coverage.

APPLICATION

Apply with brush, roller, airless or air-assisted spray or other suitable method. Optimal proportioning and mixing is achieved with the use of a Raven Lining Systems approved plural component airless spray system. For best results, apply this product to concrete when its temperature is stable or falling.

COMPONENTS AND MIX RATIO

Part A Resin:Part B Curing Agent mix ratio is 3:1 by volume

THINNING

Do not thin with solvents. If lower viscosity is needed, heat unmixed material by placing the containers in hot tap water until the desired flow properties are obtained. To heat larger quantities, drum heaters or inline heaters on specialized spray equipment may be used. Unmixed material should not be heated above 150°F.

HAND MIXING

Individually mix both Part A and Part B containers prior to measuring out 3 parts of Part A to 1 part of Part B by volume into a clean disposable pail. Completely mix combined A & B for a minimum of one minute before transferring contents to a clean pail. Continue mixing at least another minute, scraping the sides and bottom, to obtain a thorough mix before application. Properly mixed material will be a uniform color without light or dark spots.

CLEAN UP

To clean tools, use acetone, MEK or xylene. To clean skin, wash immediately and thoroughly with soap and water. Refer to the Material Safety Data Sheet for additional information on health and safety.

POT LIFE

The pot life is 20 minutes for one gallon at 72°F. The working life varies depending on the amount and temperature of epoxy mixed and the ambient temperature.

CURE TIME

Thin film set time varies with substrate temperature and application thickness. Generally, the coating will be tack-free in 3 hours at 72°F and dry-hard in about 4½ hours. This product is designed for single coat applications.

ANSI/NSF 61 cure time before service is 5 hours at 72°F.

POTABLE WATER PIPELINES: After 5 hours cure at 72°F, follow standard plumbing practices for clearing sand, debris or contaminants prior to service by flushing with 72°F potable water at 2½ to 3½ gallons per minute.

SUBSTRATE TEMPERATURE

Minimum recommended substrate temperature: 50°F
Maximum recommended substrate temperature: 120°F

TEMPERATURE RESISTANCE

Maximum recommended dry temperature: 200°F. Wet temperature resistance depends on chemical concentration and exposure time.

AquataPoxy A-61

SURFACE PREPARATION

Prior to coating, the substrate must be prepared in a manner that provides a uniform, clean, sound, neutralized surface suitable for the specified coating. The substrate must be free of all contaminants, such as oil, grease, rust, scale or deposits. In general, coating performance is proportional to the degree of surface preparation.

STEEL surfaces may require “Solvent Cleaning” (SSPC-SP 1) to remove oil, grease and other soluble contaminants. Chemical contaminants may be removed according to SSPC-SP 12/NACE No. 5. Identification of the contaminants along with their concentrations may be obtained from laboratory and field tests as described in SSPC-TU 4 “Field Methods for Retrieval and Analysis of Soluble Salts on Substrates”. Surfaces to be coated should then be prepared according to SSPC-SP 5/NACE No.1 “White Blast Cleaning” for immersion service or SSPC-SP 10/NACE No. 2 “Near White Blast Cleaning” for all other service. In certain situations, an alternate procedure may be to use high (>5,000 psi) or ultrahigh (>10,000 psi) pressure water cleaning or water cleaning with sand injection and an approved rust inhibitor. The resulting anchor profile shall be 2.5-5.0 mils and be relative to the coating thickness specified.

CONCRETE AND MASONRY surfaces must be sound and contaminant-free with a surface profile equivalent to a CSP2 to CSP5 in accordance with ICRI Technical Guideline No. 03732. This can generally be achieved by abrasive blasting, shot blasting, high pressure water cleaning, water jetting, or a combination of methods.

AVAILABLE PACKAGES

Available in 5 gallon pails (20 gallon kit), 30 gallon drums (120 gallon kit) and 55 gallon drums (220 gallon kit). Kits are supplied in the correct proportions of A & B; these two components must be mixed together before use. AquataPoxy A-61 is available through Raven Certified Applicators.

SHELF LIFE AND STORAGE

Product shelf life is 1 year from purchase date in sealed, unmixed containers, stored in a sheltered area between 60°F and 80°F (15°C and 27°C).

SAFETY

Consult the Material Safety Data Sheet for this product concerning health and safety information before using. Strictly follow all notices on the Material Safety Data Sheet and container label. If you do not fully understand the notices and procedures provided on the MSDS or if you cannot strictly comply with them, do not use this product. Actual safety measures are dependent on application methods and work environment. Contact Raven Lining Systems to obtain a copy of the Material Safety Data Sheet at 800-324-2810.

CERTIFICATIONS

Potable Water: AquataPoxy A-61 is certified to the requirements of ANSI/NSF 61 - Drinking Water System Components.

AWWA: AquataPoxy A-61 meets the physical and performance requirements of ANSI/AWWA C 210, “Liquid Epoxy Coating Systems for the Interior and Exterior of Steel Water Pipelines”.

TYPICAL PROPERTIES⁽¹⁾

DESCRIPTION	METHOD	RESULT
Tensile Strength	ASTM D 638	7,700 psi
Tensile Ultimate Elongation	ASTM D 638	1.2%
Compressive Strength	ASTM D 695	16,600 psi
Flexural Strength	ASTM D 790	10,600 psi
Hardness, Shore D	ASTM D 2240	88
Adhesion, Concrete	ASTM D 4541	Substrate Failure
Adhesion, Steel (SSPC-SP 10)	ASTM D 4541	>2,500 psi

(1) Typical properties are to be considered as representative of current production and should not be construed as specifications.

Warranty and Disclaimer: Raven Lining Systems, Inc. (“Raven”) warrants its products to be free of manufacturing defects in accord with applicable Raven quality control procedures and that they meet the formulation standards of Raven. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. If, within one year from purchase, any product is proven defective, Raven, at its sole option, will either replace the defective product or refund the purchase price. This warranty is void if the product is used contrary to Raven’s written directions.

THE AFORESAID IS THE EXCLUSIVE WARRANTY AND IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THERE IS NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL RAVEN LINING SYSTEMS BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES OR FOR LOST PROFITS. NO ACTION AGAINST RAVEN LINING SYSTEMS MAY BE COMMENCED MORE THAN ONE YEAR AFTER THE CLAIM ARISES.